

# TexNov



## ***VOLCANO***

### ***Metallic glossy acrylic finish coat interior / exterior***

**TexNov Volcano** is a metallic finish acrylic coating, use on exterior and interior wall. Manufactured as a premixed paste the product is free of dust or other foreign matter. Its formula allows it a perfect adhesion, a very high resistance to alkalis and ultraviolet rays.

**TexNov Volcano** has an integrated texture with the metallic color in a single product applicable to the trowel. This feature sets it apart from other existing metal coatings.

**TexNov**

Acrylic Coatings  
Manufacturer

# TEXNOV VOLCANO

*Metallic glossy acrylic finish coat interior / exterior*

## 1-Product description:

**TexNov Volcano** is a metallic finish acrylic coating, use on exterior and interior wall. Manufactured as a premixed paste the product is free of dust or other foreign matter. Its formula allows it a perfect adhesion, a very high resistance to alkalis and ultraviolet rays.

The installation of **TexNov Volcano** must be done by a qualified and experienced applicator in this type of finish. To learn more about product installation contact your **TexNov** representative.

The composition of **TexNov Volcano** includes pearlescent pigments of selected granulometries for a metallic finish. The shimmering effect obtained will vary according to the lighting and the angle of observation. Note that the coating will not be opaque completely.

**TexNov Volcano** has an integrated texture with the metallic color in a single product applicable to the trowel. This feature sets it apart from other existing metal coatings.

**TexNov Volcano** is available in a limited range of 10 colors and custom colors for your project. A delay of 3 weeks is required for custom colors. Contact your **TexNov** sales representative to access the samples.

**TexNov Volcano** is made of lightweight material, has zero toxicity, is free of asbestos fiber and is permeable to water vapor.

**TexNov Volcano** is a 100% acrylic resin coating with inorganic pigments, fungicides, preservatives and high performance stabilizers.

## 2-Covered area

An 18.9 L container covers approximately 140 to 160 ft<sup>2</sup> (13 to 15 m<sup>2</sup>)

## 3-Mixture

Mix the contents well using a low speed drill equipped with a vane mixer. If necessary, use **TexNov Diluent** to dilute the mixture. Otherwise clean water may be added to the **TexNov Volcano** mixture to facilitate its application. Do not add too much water that could make it difficult to apply the product and affect its performance, maximum of 500 ml (2 cups).

## 4-Installation

**TexNov Volcano** must be applied away from the fiery sun and bad weather. Ambient air, coating and surface temperatures must be above 41°F (5°C) during application and 24 hours after application.

**TexNov Volcano** is designed to be applied by trowel or with a gravity rifle. Using a steel trowel for rolling will give a more even finish while a plastic trowel will give a more textured finish.

Temporary protection : As long as the finishing coat and drying have not been completed, protect the wall against weather and other possible damage. If the temperature is below 5°C (41°F), it is important to keep the heat to a minimum or more.

Surface Preparation : The surface must be clean and free from grease, oil or other products that may impair the adhesion of the coating. The application of a layer of **TexPro FlexTex** is mandatory to obtain the necessary opacity. The application of **TexPro FlexTex** also allows to delay the drying of the finishing plaster in periods of intense heat.

Visible imperfections after basecoat drying should be sandblasted.

## 5-Product storage

**TexNov Volcano** should be stored at 5°C (41°F) or above in tightly sealed containers. Keep away from frost. The shelf life of the product is 1 year.

## 6-Transport conditions

Regulatory name : Not applicable.  
TDG Classification : Not regulated.

*Note : This product does not require any special measures during International transport.*

Properties of the mixture	
C.O.V. (Volatile organic compounds in g / L) Calculated	19

<b>TexNov Volcano performance</b>	
<b>Test Requirement</b>	<b>Result</b>
<b>Adhesion of laminate *1 CCMC 5.3.3 / ASTM D1623</b> ≥ 0.1 MPa	0.43 MPa
<b>Vapor permeability</b> ASTM E-96	10.0 perms*2
<b>Water absorption of laminate *1</b> <b>48 hrs CCMC 5.3.6</b> ≥ 20%	11.8%
<b>Accelerated aging resistance</b> <b>CCMC 5.4.6 / ASTM G154</b> No adverse effects 2000 h	Successful
<b>Durability under cyclic environmental conditions of laminate *1 CCMC 5.5.2 / ASTM E331</b> No adverse effects	Successful
<b>Mold resistance CCMC 5.3.7 / ASTM C1338</b> No Mold Formation	Successful
<b>Water tightness 2h CCMC 5.3.5</b> ≥90% waterproof	Successful
<b>Resistance to wind load</b> ASTM E-330-7	100 PSF
<b>Salin air resistance</b> ASTM B117 (hours)	5% -300
<b>Thaw Gel Resistance</b> ASTM C292-MDF	60 cycles

\*1 The laminate = **TexPro Base Express + TexNov Volcano**

\*2 Test performed at the **TexNov** laboratory according to ASTM